



20/40

This is Tier 1, natural frac sand. It's sub-angular shape, monocrystalline structure, and ISO compliant sizing create a product with superior conductivity and crush resistance compared to other silica sands.

APPLICATIONS AND BENEFITS

- For use in oil and gas wells: enhanced conductivity and crush resistance to minimize production declines over time
- For use in industrial and recreation applications: spherical silica sand that is less abrasive and provides better drainage

Closure Stress
Up to 7,000 psi
(48.3 MPa)

Maximum Recommended Temp
250°F
(121°C)

PHYSICAL PROPERTIES

Mesh Size	Specific Gravity	Bulk Density lb/ft3	Bulk Density g/cm3	Kumbein Roundness	Kumbein Sphericity	Turbidity (NTU)	Crush Resistance K-Value
20/40	2.65	96.23	1.53	0.6	0.7	104	7K

CONDUCTIVITY (MD/FT), 50 HOURS @ 150 DEGREES F

Closure Stress	2,000	4,000	6,000	8,000
20/40	15,617	2,522	1,241	455

For more information contact sales@silicaservicesinc.com

GRADE NUMBERS INDICATE RELATIVE VALUES OR RESULTS. THEY ARE NOT A SPECIFICATION OR WARRANTY OF PERFORMANCE.

HEALTH HAZARD WARNING: Prolonged inhalation of dust associated with the materials described in this data sheet can cause delayed lung injury including Silicosis, a progressive, disabling and sometimes fatal lung disease. IARC and NTP have determined that crystalline silica can cause lung cancer in humans. Risk of injury is dependent on the duration and level of exposure. Follow OSHA or other relevant safety and health standards for the form of crystalline silica called Quartz. Current safety data sheet, containing safety information, is available and should be consulted before usage.

Notice: While information contained herein is correct to the best of our knowledge, Silica Services hereby disclaims any warranties as to the accuracy of the same. Recommendations or suggestions are made without guarantee or representation as to result, since conditions of usage are beyond our control. All materials are sold subject to Silica Services's standard terms and conditions of sale and the condition that buyer shall make his own tests to determine the suitability of such product for buyer's purpose. No statement contained herein shall be construed as a license to operate under or as a recommendation to infringe any patent. All information contained herein is subject to change without notice.

Silica/Silica Containing

Copyright © 2019 Silica Services, LLC. All rights reserved.